

Ultramid® HMG13 HS BK-102

Polyamide 6



Product Description

Ultramid HMG13 HS BK-102 is a 63% glass reinforced, injection molding, high modulus nylon designed to have high strength and stiffness for metal replacement applications. It also has excellent moldability and outstanding surface appearance.

Applications

Potential applications are mirror brackets, fuel lids, gas-assisted steering wheel inserts, ski bindings and bike rack clamps.

| PHYSICAL | ISO Test Method | Property Value | |
|--|-----------------|----------------|-------------|
| Density, g/cm | 1183 | 1.74 | |
| MECHANICAL | ISO Test Method | Dry | Conditioned |
| Tensile Modulus, MPa | 527 | | |
| 23C | | 22,000 | 13,400 |
| Tensile stress at break, MPa | 527 | | |
| 23C | | 235 | 155 |
| Tensile strain at break, % | 527 | | |
| 23C | | 2 | - |
| Flexural Strength, MPa | 178 | | |
| 23C | | 355 | - |
| Flexural Modulus, MPa | 178 | | |
| 23C | | 19,000 | - |
| IMPACT | ISO Test Method | Dry | Conditioned |
| Izod Notched Impact, kJ/m ² | 180 | | |
| 23C | | 15 | - |
| Charpy Notched, kJ/m ² | 179 | | |
| 23C | | 15 | - |
| -30C | | 13 | - |
| Charpy Unnotched, kJ/m ² | 179 | | |
| 23C | | 90 | - |
| -30C | | 90 | - |
| THERMAL | ISO Test Method | Dry | Conditioned |
| Melting Point, C | 3146 | 220 | - |
| HDT A, C | 75 | 214 | - |
| UL RATINGS | UL Test Method | Property Value | |
| Flammability Rating, 1.5mm | UL94 | HB | |
| Relative Temperature Index, 1.5mm | UL746B | | |
| Mechanical w/o Impact, C | | 130 | |
| Mechanical w/ Impact, C | | 105 | |
| Electrical, C | | 130 | |



Max. Water content: 0.03%

Although Product is supplied in sealed containers, drying is recommended in applications requiring optimum surface aesthetics. A dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 300-320 degC (572-608 degF)

Mold Temperature 80-95 degC (176-203 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Rear Zone 275-300 degC (527-572 degF)

Center Zone 285-310 degC (545-590 degF)

Front Zone 300-325 degC (572-617 degF)

Nozzle 300-325 degC (572-617 degF)

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95 degC (176-203 degF) is required.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel.

Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage. recommended to minimize glass fiber breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

