

Ultramid® A3W BK00464

Polyamide 66



Product Description

Ultramid A3W BK00464 is an easy flowing, pigmented black, heat aging resistant injection molding PA66 grade for fast processing.

Applications

Typical applications include highly stressed parts such as bearings, bearing cages, gear-wheels, coil formers and cable connectors.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm	1183	1.13	
Moisture, %	62		
(50% RH)		2.8	
(Saturation)		8.5	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		3,290	-
Tensile stress at yield, MPa	527		
23C		90	-
Tensile strain at yield, %	527		
23C		4.5	-
Flexural Modulus, MPa	178		
23C		3,130	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²	180		
23C		5	-
-40C		3.5	-
Charpy Notched, kJ/m ²	179		
23C		5	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	260	-
HDT A, C	75	69	-

Processing Guidelines

Material Handling

Max. Water content: 0.20%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 280-300 degC (536-572 degF)

Mold Temperature 40-80 degC (104-176 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)



Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 40-80 degC (104-176 degF) is recommended.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing.

