Product Information

Ultramid[®] A3EG7 BK00564 Polyamide 66



Product Description

Ultramid A3EG7 BK00564 is a 35% glass fiber reinforced, pigmented black, injection molding PA66 grade for machinery components and housings of high stiffness and dimensional stability.

Applications

Typical applications include lamp socket housings, cooling fans, insulating profile for aluminium window frames, water containers for automotive cooling systems, as well as electrically insulating parts.

Density, g/cm			Property Value	
	1183	1.41		
Moisture, %	62			
(50% RH)		1.6		
(Saturation)		5		
MECHANICAL	ISO Test Method	Dry	Conditioned	
Tensile stress at break, MPa	527			
23C		190	-	
Tensile strain at break, %	527			
23C		2.8	-	
Flexural Modulus, MPa	178			
23C		10,000	-	
IMPACT	ISO Test Method	Dry	Conditioned	
Izod Notched Impact, kJ/m ²	180			
23C		9.5	-	
THERMAL	ISO Test Method	Dry	Conditioned	
Melting Point, C	3146	260	-	
HDT A, C	75	250	-	





Ultramid® A3EG7 BK00564



Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



