

Ultramid® A3XG3 BK20562

Polyamide 66

Product Description

Ultramid A3XG3 BK20562 is a 15% glass fiber reinforced injection molding PA66 grade with improved flame retardance and enhanced long-term heat stability. The grade is based on red phosphorous and exhibits exceptional mechanical properties and outstanding surface finish. Flame performance has been determined to be V0 at 0.8mm per the UL94 method.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm	1183	1.34	
Mold Shrinkage, parallel, %	294-4	0.5	
Mold Shrinkage, normal, %	294-4	1.1	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		6,735	4,445
Tensile stress at break, MPa	527		
23C		120	72
Tensile strain at break, %	527		
23C		2.8	5.6
Flexural Strength, MPa	178		
23C		183	125
Flexural Modulus, MPa	178		
23C		6,145	4,085
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²	180		
23C		4.8	5
-40C		4.5	3.8
Charpy Notched, kJ/m ²	179		
23C		4.8	5.6
-30C		4.2	4.0
Charpy Unnotched, kJ/m ²	179		
23C		45	49
-30C		35	23
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	260	-
HDT A, C	75	222	-
HDT B, C	75	250	-

Processing Guidelines

Material Handling
 Max. Water content: 0.05%



Special handling and safety precautions must be used when processing this grade of material. Please contact your BASF Technical Service Representative for details. Product is supplied in moisture barrier packaging. However, further drying is typically required. A dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF Technical Service representative.

Typical Profile

Melt Temperature 285-300 degC (545-572 degF)

Mold Temperature 80-90 degC (176-194 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95 degC (176-203 degF) is required.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel.

Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

