

#### Product description

Ultramid® ONE JL 218 V50 Natural is a modified high temperature polyamide reinforced with 50% of glass fiber, heat stabilized, for injection molding.  
This product offers strong benefits in term of productivity and excellent surface aspect. Also, this grade has high mechanical properties, high heat deflection temperature, moisture resistance and dimensional stability.  
The results shown are based on an experimental grade. These results will be further enhanced and improved as more industrial lots are produced and statistical data are available.

#### Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

##### Injection Advice:

- For reinforced polyamides, BASF SE recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

#### Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and BASF SE is at their disposal to supply any additional information.

#### Safety Information

Detailed information regarding safety are available on the safety data sheet (MSDS). MSDS is sent with the first material order or available by contacting our customer services

#### Regulations Compliance

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with RoHS Directive 2011/65/EU, 2015/863 and local regulations as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

#### Customer Services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design



Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>General Properties</b>			
South and Central America	-	-	<b>+</b>
Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)	-	-	<b>M</b>
Colour: black (bk), uncoloured (un), coloured (co), transparent (tr)	-	-	<b>un</b>
Pellets	-	-	<b>+</b>
<b>Physical</b>			
Molding shrinkage (parallel)	ISO 294-4	%	<b>0.70</b>
Molding shrinkage (normal)	ISO 294-4	%	<b>0.90</b>
Water absorption, 24 h in water, 23 °C	ISO 62	%	<b>0.5</b>
Water absorption, equilibrium in water at 23°C	similar to ISO 62	%	<b>2.6</b>
Density	ISO 1183	kg/m <sup>3</sup>	<b>1600 / -</b>
<b>Mechanical properties</b>			
			<b>dry / cond.</b>
Tensile modulus	ISO 527-1/-2	MPa	<b>17500 / -</b>
Stress at break	ISO 527-1/-2	MPa	<b>230 / -</b>
Strain at break	ISO 527-1/-2	%	<b>1.5 / -</b>
Flexural modulus	ISO 178	MPa	<b>14500 / -</b>
Flexural strength	ISO 178	MPa	<b>270 / -</b>
Charpy notched impact strength ISO 179/1eA (23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	<b>10 / -</b>
Charpy impact strength ISO 179-1eU (23°C)	ISO 179/1eU	kJ/m <sup>2</sup>	<b>80 / -</b>
<b>Thermal properties</b>			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	<b>268</b>
Melting temperature, DSC (10°C/min)	ISO 11357-1/-3	°C	<b>292</b>
<b>Flammability</b>			
Burning Behav. at 1.6 mm nom. thickn.	IEC 60695-11-10	class	<b>V-2</b>
Burning Behav. at thickness 0.8 mm	IEC 60695-11-10	class	<b>V-2</b>
Burning Behav. at thickness 3.2 mm	UL-94, IEC 60695	class	<b>V-2</b>
Glow Wire Flammability Index (0.8 mm)	IEC 60695-2-12	°C	<b>850</b>
Glow Wire Flammability Index (1.6 mm)	IEC 60695-2-12	°C	<b>850</b>
Glow Wire Flammability Index (3.2 mm)	IEC 60695-2-12	°C	<b>850</b>
<b>Injection</b>			
Pre/Post-processing, Pre-drying, Temperature	-	°C	<b>80</b>
Pre/Post-processing, max. allowed water content	-	%	<b>0.15</b>
Injection molding cylinder temperature 1 (feed zone)	-	°C	<b>290 - 300</b>
Injection molding cylinder temperature 2 (compression)	-	°C	<b>295 - 310</b>
Injection molding cylinder temperature 3 (metering-zone, head room of screw)	-	°C	<b>300 - 320</b>
injection molding, Mold temperature, range	ISO 294	°C	<b>90 - 110</b>

