

Ultradur® B 4300 G6

PBT (Polybutylene Terephthalate)



Product Description

Ultradur B 4300 G6 is an easy flowing injection molding PBT with 30% glass fiber reinforcement for rigid, tough, and dimensionally stable parts.

Applications

Typical applications include windshield wiper arms, printed circuit boards, housings, consoles, contact carriers, and covers.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm	1183	1.53
Viscosity Number, cm/g	1628	102
Mold Shrinkage, parallel, %	294-4	0.34
Mold Shrinkage, normal, %	294-4	1.07
Moisture, %	62	
(50% RH)		0.2
(Saturation)		0.4
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (250 C/2.16 Kg), cc/10min.	1133	11
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		10,000
Tensile stress at break, MPa	527	
-40C		204
23C		135
Tensile strain at break, %	527	
23C		2.5
Flexural Strength, MPa	178	
23C		200
Flexural Modulus, MPa	178	
23C		8,800
Tensile Creep Modulus (1000h), MPa	899	7,500
IMPACT	ISO Test Method	Property Value
Charpy Notched, kJ/m ²	179	
23C		11
Charpy Unnotched, kJ/m ²	179	
23C		67
-30C		74
THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	223
HDT A, C	75	215
HDT B, C	75	220
Coef. of Linear Thermal Expansion, Parallel, mm/mm C		0.25 X10-4



ELECTRICAL	ISO Test Method	Property Value
Comparative Tracking Index	IEC 60112	375
Volume Resistivity	IEC 60093	>1E13
Surface Resistivity	IEC 60093	1E13
Dielectric Constant (100 Hz)	IEC 60250	4
Dielectric Constant (1 MHz)	IEC 60250	3.8
Dissipation Factor (100 Hz)	IEC 60250	25
Dissipation Factor (1 MHz)	IEC 60250	170
UL RATINGS	UL Test Method	Property Value
Flammability Rating, 1.5mm	UL94	HB
Relative Temperature Index, 1.5mm	UL746B	
Mechanical w/ Impact, C		105
Electrical, C		130

Processing Guidelines

Material Handling

Max. Water content: 0.04%

To ensure optimum part performance, this product must be dried prior to molding and maintained at a moisture level of less than 0.04%. Dehumidifying or desiccant dryers operating at 100-120 degC (212-248 degF) for 4 hours drying time are recommended. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 250-270 degC (482-518 degF)

Mold Temperature 60-100 degC (140-212 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over mold temperatures of 60-100 degC (140-212 degF); however, for optimizing surface appearance, dimensional stability and part performance, mold surface temperatures of at least 80 degC (176 degF) are preferred.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel.

Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 10 bar (145 psi) is recommended due to the risk of excessive shear.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

