

Ultrason® E 6020 P

Polyether Sulfone (PES)



Product Description

Ultrason E 6020 P is an unfilled, injection molding PES grade.

Applications

Typical applications include membrane applications and coatings.

PHYSICAL	ISO Test Method	Property Value
Moisture, %	62	
(50% RH)		1
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		2,700
Tensile stress at yield, MPa	527	
23C		90
Tensile strain at yield, %	527	
23C		6.7
THERMAL	ISO Test Method	Property Value
HDT A, C	75	207

