

# Petra® 130 BK-112

## PET (Polyethylene Terephthalate)



### Product Description

Petra 130 BK-112 is a 30% glass fiber reinforced, black pigmented polyethylene terephthalate injection molding compound. It exhibits a superb combination of performance properties including good strength and stiffness at elevated temperatures. It also has good chemical resistance and dimensional stability, and adequate ductility for most applications.

### Applications

Petra 130 BK-112 is generally recommended for applications such as automotive door lock components, housings, gears and electrical and mechanical components.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm	1183	1.55
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		10,200
Tensile stress at break, MPa	527	
-40C		211
23C		145
121C		54
Tensile strain at break, %	527	
23C		3
Flexural Modulus, MPa	178	
23C		8,250
IMPACT	ISO Test Method	Property Value
Izod Notched Impact, kJ/m <sup>2</sup>	180	
23C		9.5
-40C		8.5
Charpy Notched, kJ/m <sup>2</sup>	179	
23C		9
-30C		8.5
THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	245
HDT A, C	75	210
HDT B, C	75	240
ELECTRICAL	ISO Test Method	Property Value
Volume Resistivity	IEC 60093	>1E13
UL RATINGS	UL Test Method	Property Value
Flammability Rating, 1.5mm	UL94	HB
Relative Temperature Index, 1.5mm	UL746B	
Mechanical w/o Impact, C		140
Mechanical w/ Impact, C		140
Electrical, C		140



## Processing Guidelines

### Material Handling

Max. Water content: 0.02%

To ensure optimum part performance, this product must be dried prior to molding and maintained at a moisture level of less than 0.02%, with a preferred moisture target of less than 0.015%. A dehumidifying hopper dryer mounted on the molding machine and equipped with alternating desiccant beds and air temperature/dew point indicators is recommended. Drying time is 2 - 4 hours at 120 degC (248 degF). Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

### Typical Profile

Melt Temperature 280-300 degC (536-572 degF)

Mold Temperature 100-110 degC (212-230 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

### Mold Temperatures

This product can be processed over mold temperatures of 80-120 degC; however, for optimizing surface appearance, dimensional stability and part performance, mold surface temperatures of 100-110 degC (212-230 degF) are preferred.

### Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel.

Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage. recommended to minimize glass fiber breakage.

### Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

