

Ultraform® N 2650 Z6

Polyoxymethylene

PHYSICAL	ISO Test Method	Property Value
Density, g/cm	1183	1.33
Moisture, %	62	
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (190 C/2.16 Kg), cc/10min.	1133	7
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		1,200
Tensile stress at yield, MPa	527	
23C		38
Tensile stress at break, MPa	527	
Tensile strain at yield, %	527	
23C		19
Nominal strain at break, %	527	
23C		44
Flexural Strength, MPa	178	
Flexural Modulus, MPa	178	
Tensile Creep Modulus (1000h), MPa	899	400
IMPACT	ISO Test Method	Property Value
Izod Notched Impact, kJ/m ²	180	
Charpy Notched, kJ/m ²	179	
23C		20
-30C		9
Charpy Unnotched, kJ/m ²	179	
23C		N
-30C		240
THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	166
HDT A, C	75	75
Coef. of Linear Thermal Expansion, Parallel, mm/mm C		1.4 X10-4
ELECTRICAL	ISO Test Method	Property Value
Comparative Tracking Index	IEC 60112	600
Volume Resistivity	IEC 60093	1E11
Surface Resistivity	IEC 60093	1E12
Dielectric Constant (1 MHz)	IEC 60250	4.4
Dissipation Factor (1 MHz)	IEC 60250	200

