

Elastollan® 1185A10W

Technical Bulletin

Polyether Type

Elastollan® 1185A10W is a polyether-based thermoplastic polyurethane (TPU). It is specifically formulated for wire and cable, film and sheet, and extruded profile applications. It contains a non-halogenated flame retardant and has a UL-94 V2 vertical flame rating. It also passes FAR 25.853(A) flame test. It exhibits excellent abrasion resistance, toughness, transparency, low temperature properties, hydrolytic stability and fungus resistance. As with all TPU products, Elastollan® 1185A10W must be dried before processing. The drying step is required to maintain a low moisture content until the product enters the processing equipment. The water content must be less than 0.03% before and during processing. The typical drying conditions should be 2-4 hours @ 160°-180°F (70°-85°C). Elastollan® 1185A10W can be stored for up to 1 year in its original container. Containers should be stored in a cool and dry area.

Properties		Test Method	Typical Value	
			English	SI
Physical				
Specific Gravity	gr./cm ³	ASTM D-792	1.16	1.16
Hardness	Shore A	ASTM D-2240	83A	83A
Flame Rating		UL-94	V2 - .032" - .120"	V2 – 0.75mm – 3mm
LOI	%	ASTM D-2863	23%	23%
Mechanical				
Tensile Strength (Ultimate)	psi / MPa	ASTM D-412	7500 psi	38 MPa
Tensile Stress	@100% Elong.	ASTM D-412	850 psi	5.9 MPa
Tensile Stress	@300% Elong.	ASTM D-412	1900 psi	13 MPa
Elongation at Break	%	ASTM D-412	595%	595%
Tensile Set	@200% Elong.	ASTM D-412	71%	71%
Compression Set, %	22 hrs @ 23°C	ASTM D-395 (B)	25%	25%
Compression Set, %	22 hrs @ 70°C	ASTM D-395 (B)	45%	45%
Flexural Modulus	psi / MPa	ASTM D-790	6250 psi	43 MPa
Tear Strength	lb./in. N/mm	ASTM D-624, Die C	500 lb./in.	88 N/mm
Taber Abrasion Resistance / mg loss	1000 gr./H-18	ASTM D-1044	35 mg	35 mg
Thermal				
Vicat Softening Point	°F/°C	ASTM D-1525	212 °F	100 °C
Glass Transition Temperature	°F/°C	DSC	-46 °F	-43 °C
Processing Conditions, Extrusion	°F/°C		340 - 365 °F	170 - 180 °C
Processing Conditions, Inj. Molding	°F/°C		340 - 375 °F	170 - 190 °C

The above values are shown as typical values and should not be used as specifications.
Molded plaques 0.080" thick were cured 20 hours at 100 °C before testing

BASF

