

Elastollan® S85A55N

Technical Bulletin

Polyester Type

Elastollan® S85A55N is a polyester-based thermoplastic polyurethane (TPU). It exhibits excellent abrasion resistance and toughness, good heat, oil, fuel, and solvent resistance. As with all TPU products, Elastollan S85A55N must be dried before processing. The drying step is required to both dry the granules and also maintain a low moisture content until the product enters the processing equipment. The water content must be less than 0.03% before processing. The typical drying conditions should be 2-4 hours @ 175°-195°F (80°-90°C). Elastollan S85A55N can be stored for up to 1 year in its original container. Containers should be stored in a cool and dry area.

Properties		Test Method	Typical Value	
			English	SI
Physical				
Specific Gravity	gr./cm ³	ASTM D-792	1.22	1.22
Hardness	Shore A	ASTM D-2240	85A	85A
Mechanical				
Tensile Strength (Ultimate)	psi / MPa	ASTM D-412	4900 psi	33.8 MPa
Tensile Stress	@100% Elong.	ASTM D-412	1000 psi	6.9 MPa
Tensile Stress	@300% Elong.	ASTM D-412	1980 psi	13.7 MPa
Elongation at Break	%	ASTM D-412	690 %	690 %
Compression Set, %	22 hrs@ 23°C	ASTM D-395 (B)	25%	25%
Compression Set, %	22 hrs@ 70°C	ASTM D-395 (B)	35%	35%
E-Modulus	psi / MPa	ASTM D-412	2100 psi	14.5 MPa
Tear Strength	lb./in. N/mm	ASTM D-624, Die C	590 lb./in.	104 N/mm
Taber Abrasion Resistance / mg loss	1000 gr./H-18	ASTM D-1044	25 mg	25 mg
DIN Abrasion Resistance	mm ³ loss	DIN 53516	35 mm ³	35 mm ³
Thermal				
Vicat Softening Point	°F/°C	ASTM D-1525	225 °F	107 °C
Glass Transition Temperature	°F/°C	DSC	-4 °F	-20°C
Processing Conditions, Extrusion	°F/°C		360 - 400 °F	180 - 205 °C
Processing Conditions, Inj. Molding	°F/°C		365 - 410 °F	185 - 210 °C

The above values are shown as typical values and should not be used as specifications.
Molded plaques 0.080" thick were cured 20 hours at 100 °C before testing

BASF

