

Marlex® 9012 Polyethylene

HIGH DENSITY POLYETHYLENE (HDPE)

This high density polyethylene is an ethylene-hexene copolymer that is tailored for injection molded applications that require:

- Good flow
- Good impact strength
- Good stiffness
- Durability

This resin meets these specifications:

- ASTM D4976 - PE 232
- FDA 21 CFR 177.1520(c) 3.2a, use conditions B through H per 21 CFR 176.170(c)

Typical injection molded applications for 9012 include:

- Food pails (two- and five-gallon)
- Automotive applications
- Toys
- Closures
- Housewares

Nominal Physical Properties ⁽¹⁾	English	SI	Method
Density	---	0.952 g/cm ³	ASTM D1505
Flow Rate (MI, 190 °C/2.16 kg)	---	11.5 g/10 min	ASTM D1238
Tensile Strength at Yield , 2 in/min, Type IV bar	3,900 psi	27 MPa	ASTM D638
Elongation at Break , 2 in/min, Type IV bar	900 %	900 %	ASTM D638
Flexural Modulus , Tangent - 16:1 span:depth, 0.5 in/min	185,000 psi	1,270 MPa	ASTM D790
ESCR , Condition B (100 % Igepal), F ₅₀	15 h	15 h	ASTM D1693
Durometer Hardness , Type D (Shore D)	63	63	ASTM D2240
Vicat Softening Temperature , Loading 1, Rate A	255 °F	124 °C	ASTM D1525
Brittleness Temperature , Type A, Type I specimen	< -103 °F	< -75 °C	ASTM D746

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1.

