

PREMIUM EXTRUSION AND RIGID PACKAGING RESINS

FDA 21 CFR 177.1520(c) 2.2, use conditions B through H

## Marlex<sup>®</sup> 1122B

•

This resin meets these specifications:

ASTM D4976 - PE 113

per 21 CFR 176.170(c)

## This autoclave LDPE homopolymer is tailored for applications that require:

- Excellent flexibility
- Moderate flow
- Moderate warpage resistance

## Typical injection molded applications for 1122B include items such as:

- Healthcare product closures
- Charcoal lighter fluid closures
- Champagne bottle stoppers

NOMINAL PHYSICAL PROPERTIES <sup>(1)</sup>	English	SI	Method
Density		0.920 g/cm <sup>3</sup>	ASTM D1505
Melt Index, 190/2.16		2.1 g/10 min	ASTM D1238
Tensile Strength at Yield, 2 in/min, Type IV bar	1,500 psi	10 MPa	ASTM D638
Elongation at Break, 2 in/min, Type IV bar	500%	500%	ASTM D638
Flexural Modulus, Tangent - 16:1 span:depth, 0.5 in/min	40,000 psi	270 MPa	ASTM D790
Durometer Hardness, Type D (Shore D)	50	50	ASTM D2240
Vicat Softening Temperature, Loading 1, Rate A	200°F	93°C	ASTM D1525
Brittleness Temperature, Type A, Type I specimen	<-103°F	<-75°C	ASTM D746

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1.

Another quality product from





