

MarFlex® 1017

EXTRUSION COATING GRADE LOW DENSITY POLYETHYLENE

This LDPE is tailored for applications that require:

- Excellent processability
- Low neck-in
- High temperature extrusion stability

Typical extrusion coating applications may include:

- Laminations
- Sealant resin
- General paper and board coating
- General flexible packaging

Nominal Resin Properties	English	SI	Method
Density	---	0.917 g/cm ³	ASTM D1505
Melt Index, 190C/2.16Kg	---	7 g/10min	ASTM D1238
Melting Point	218 °F	104 °C	ASTM D3418
Vicat Softening Temperature	193 °F	90 °C	ASTM D1525

Nominal Extrusion Coating Properties at 1 mil (14.4 lbs/ream) ¹	English	SI	Method
WVTR	1.38 g/100in ² /day	21 g/m ² /day	ASTM F1249
OTR	510 cm ³ /100in ² /day	8000 cm ³ /m ² /day	ASTM D3985

1. Testing performed on coated slip sheet at 14.4 lbs/ream or 1.0 mil

Another quality product from

