

PREMIUM EXTRUSION AND RIGID PACKAGING RESINS

Marlex[®] C100

METALLOCENE LINEAR LOW DENSITY POLYETHYLENE

This linear low density, hexene copolymer is tailored for blow This resin meets these specifications: molding containers that require:

- High gloss
- Good clarity ٠
- Excellent ESCR •

- ASTM D4976 PE 214 •
- FDA 21 CFR 177.1520(c) 3.2a, use conditions B through H per 21 CFR 176.170(c)

Typical blow molded applications for C100 include:

- Glossy multilayer bottles
- Squeezable bottles

| NOMINAL PHYSICAL PROPERTIES ⁽¹⁾ | English | SI | Method |
|---|------------|-------------------------|------------|
| Density | | 0.918 g/cm ³ | ASTM D1505 |
| Melt Index, 190/2.16 | | 1.0 g/10 MI | ASTM D1238 |
| Tensile Strength at Yield, 2 in/min, Type IV bar | 1,500 psi | 10 MPa | ASTM D638 |
| Elongation at Break, 2 in/min, Type IV bar | 600% | 600% | ASTM D638 |
| Flexural Modulus, Tangent - 16:1 span:depth, 0.5 in/min | 45,000 psi | 310 MPa | ASTM D790 |
| ESCR, Condition A (100% Igepal), F50 | >1,000 h | >1,000 h | ASTM D1693 |
| ESCR, Condition B (100% Igepal), F50 | >1,000 h | >1,000 h | ASTM D1693 |
| Brittleness Temperature, Type A, Type I specimen | <-103°F | <-75°C | ASTM D746 |

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1.

Another quality product from



The Woodlands, Texas



