

Marlex® D143FK Polyethylene

METALLOCENE LINEAR LOW DENSITY POLYETHYLENE (mLLDPE)

This metallocene linear low density polyethylene is an ethylene-hexene copolymer tailored for blown film applications that require:

- Superb clarity
- Excellent gloss
- Exceptional toughness
- Outstanding heat seal

Typical blown film applications include:

- Seal layer in coextrusions
- Heavy duty packaging
- Clarity packaging

Nominal Resin Properties	English	SI	Method
Melt Index, 190 °C/2.16 kg	---	1.4 g/10 min	ASTM D1238
Density	---	0.916 g/cm ³	ASTM D1505
Slip	1000 ppm	1000 ppm	---
Antiblock	5000 ppm	5000 ppm	---
Process Aid	Yes	Yes	---

Nominal Blown Film Properties at 1 mil ¹	English	SI	Method
Haze	9 %	9 %	ASTM D1003
Gloss, 60°	105	105	ASTM D2457
COF	0.15	0.15	ASTM D1894
Dart	---	580 g/mil	ASTM D1709
Elmendorf Tear MD/TD	---	170 g/mil	ASTM D1922
Elmendorf Tear MD/TD	---	370 g/mil	ASTM D1922
Tensile Strength at Yield MD/TD	1800 psi	12 MPa	ASTM D882
Tensile Strength at Yield MD/TD	1400 psi	10 MPa	ASTM D882
Tensile Strength at Break MD/TD	7500 psi	52 MPa	ASTM D882
Tensile Strength at Break MD/TD	6450 psi	44 MPa	ASTM D882
Tensile Elongation at Break MD/TD	450 %	450 %	ASTM D882
Tensile Elongation at Break MD/TD	550 %	550 %	ASTM D882
1 % Secant Modulus MD/TD	22000 psi	152 MPa	ASTM D882
1 % Secant Modulus MD/TD	22700 psi	157 MPa	ASTM D882
Seal Initiation Temperature ²	216 °F	102 °C	ASTM F88

1. Produced on a LLDPE line at 2.5:1 BUR, 80 mil die gap, 8 in die, 250 lb/h, 400 °F melt temperature.

2. Temperature at which 0.3 lb/in heat seal strength is achieved. 0.5 s dwell, 30 psi pressure, 11.8 in/min separation rate.

