

XK44

K-Resin® Styrene-Butadiene Copolymers (SBC)

Customer Benefits

- Good Clarity
- Good Stiffness
- Good Formability
- Good Toughness
- High Surface Gloss

Typical Applications

- Thermoformed Clam Shell Packaging
- Thermoformed Blister Packs
- Thermoformed Medical Trays
- Blow Molded Products

Nominal Physical Properties ⁽¹⁾	Condition	English	SI	Method
Specific Gravity	-	1.01 g/cc	1.01 g/cc	ASTM D792
Melt Flow Rate	200°C/5Kg	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Tensile Yield Strength ⁽²⁾	2.0 in/min	3130 psi	21.6 MPa	ASTM D638
Tensile Elongation @ Break ⁽²⁾	2.0 in/min	350%	350%	ASTM D638
Flexural Modulus ⁽³⁾	0.5 in/min	162,690 psi	1,122 Mpa	ASTM D790
Flexural Yield Strength ⁽³⁾	0.5 in/min	5000 psi	34.5 Mpa	ASTM D790
Deflection Temperature Under Load (DTUL)	264 psi (1.8 MPa)	127 °F	53 °C	ASTM D648
Instrumented Impact Total Energy ⁽⁴⁾	73 °F	420 in-lbs	47.5 J	ASTM D3763
Hardness, Shore D	-	65	65	ASTM D2240
Vicat Softening Point	-	168 °F	75.6 °C	ASTM D1525
Light Transmission	-	93%	93%	ASTM D1003

1. The nominal properties herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded.

2. Type 1 @ 2 in/min (50 mm/min)

3. 0.125 in (3.2 mm) specimen @ 0.5 in/sec (1.27 cm/min)

4. 0.125 in (3.2 mm) specimen @ 150 in/sec (381 cm/sec) impact rate

MEETS THESE IMPORTANT REQUIREMENTS:

- K-Resin® SBC grade XK44, as shipped by Chevron Phillips Chemical Company LP, meets the specifications of the United States FDA Food Packaging Regulation 21 CFR 177.1640 (polystyrene and rubber modified polystyrene). By virtue of this compliance, K-Resin® XK44 may be used as a component of articles for use in contact with food. There are no regulatory food type or temperature restrictions on this resin as defined under 21 CFR 176.170 (c).
- USP Class VI
- Commission Regulation (EU) No. 10/2011 and all its amendments.
- K-Resin® SBC grade XK44 is produced in an ISO 9001:2008 certified plant.

MSDS 100000000073

Another quality product from

