

Durethan® T40

PA*

Unreinforced, Injection Molding, Blow Molding Grade, Film Extrusion, Extrusion,
Transparent

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	3300 / 3000	MPa	ISO 527-1/-2
Yield stress	110 / 90	MPa	ISO 527-1/-2
Yield strain	6 / 5	%	ISO 527-1/-2
Flexural modulus	3000 / 3000	MPa	ISO 178
Flexural strength	150 / 130	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	<10 / <10	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m²	ISO 179/1eA
Izod notched impact strength (-40°C)	<10 / <10	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Temp. of deflection under load (1.80 MPa)	105 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	115 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.7 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12



Durethan® T40

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
GWFI (Thickness (1) tested)	2 / –	mm	IEC 60695–2–12
ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	4.3 / 4.6	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.8 / 4	–	IEC 62631–2–1
Dissipation factor (100 Hz)	400 / 480	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	900 / 1100	E–4	IEC 62631–2–1
Volume resistivity	1E13 / 1E13	Ohm*m	IEC 62631–3–1
Surface resistivity	* / 1E15	Ohm	IEC 62631–3–2
Electric strength	25 / 28	kV/mm	IEC 60243–1
Comparative tracking index	600 / –	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1180 / –	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	107 / *	cm³/g	ISO 307, 1157, 1628
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	80–100	°C	

