

Durethan® BKV135

PA*—I—GF35

35% Glass Reinforced, Injection Molding, Improved Impact

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	10200 / 6000	MPa	ISO 527-1/-2
Stress at break	170 / 110	MPa	ISO 527-1/-2
Strain at break	3 / 7	%	ISO 527-1/-2
Flexural modulus	9100 / 5500	MPa	ISO 178
Flexural strength	280 / 170	MPa	ISO 178
Charpy impact strength (+23°C)	100 / 110	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	85 / 85	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	20 / 30	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	20 / 28	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	213 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.9 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10



Durethan® BKV135

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Oxygen index	22 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	650 / –	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2 / –	mm	IEC 60695-2-12

ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	4 / 10	–	IEC 62631-2-1
Relative permittivity (1 MHz)	4 / 5	–	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
Electric strength	40 / 35	kV/mm	IEC 60243-1
Comparative tracking index	600 / –	V	IEC 60112

OTHER PROPERTIES	DRY / COND		
Water absorption	6.5 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1410 / –	kg/m³	ISO 1183

MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	134 / *	cm³/g	ISO 307, 1157, 1628

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260-290	°C	
Mold temperature	80-100	°C	

