

Durethan® BKV230H2.0

PA*—I—GF30

30% Glass Reinforced, Injection Molding, Heat Stabilized, Improved Impact

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	0.7 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	8100 / 4400	MPa	ISO 527-1/-2
Stress at break	130 / 80	MPa	ISO 527-1/-2
Strain at break	4 / 8	%	ISO 527-1/-2
Flexural modulus	7300 / 4100	MPa	ISO 178
Flexural strength	220 / 115	MPa	ISO 178
Charpy impact strength (+23°C)	90 / 100	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	95 / 95	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	25 / 45	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	20 / 20	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	25 / 35	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	213 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	200 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.3 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10



Durethan® BKV230H2.0

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Glow Wire Flammability Index GWFI	650 / –	°C	IEC 60695–2–12
GWFI (Thickness (1) tested)	2 / –	mm	IEC 60695–2–12
ELECTRICAL PROPERTIES			
	DRY / COND		
Comparative tracking index	450 / –	V	IEC 60112
OTHER PROPERTIES			
	DRY / COND		
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1320 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS			
	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–290	°C	
Mold temperature	80–100	°C	

