

Akulon[®] XS236-C

PA6

High Viscosity, Lubricated

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	218 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Water absorption	9.5 / *	%	Sim. to ISO 62
Humidity absorption	2.5 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	244 / *	cm³/g	ISO 307, 1157, 1628

