

Durethan® B31SH2.0

PA6

Injection Molding, Unreinforced, Heat Stabilized

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage (parallel)	1.4 / *	%	ISO 294-4
Molding shrinkage (normal)	1.4 / *	%	ISO 294-4
MECHANICAL PROPERTIES	DRY / COND		
Tensile modulus	3400 / –	MPa	ISO 527-1/-2
Yield stress	70 / –	MPa	ISO 527-1/-2
Yield strain	2.5 / –	%	ISO 527-1/-2
Flexural modulus	2900 / –	MPa	ISO 178
Flexural strength	115 / –	MPa	ISO 178
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	60 / *	°C	ISO 75-1/-2
OTHER PROPERTIES	DRY / COND		
Density	1140 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260-280	°C	



Property Data

Durethan® B31SH2.0

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Mold temperature	80–100	°C	

