

Akulon[®] Ultraflow XG—FKGS6/A

PA6—GF30 FR(40)

30% Glass Reinforced, Flame Retardant (halogen free)

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage [parallel]	0.2 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	0.6 / *	%	Sim. to ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	10800 / —	MPa	ISO 527-1/-2
Stress at break	130 / —	MPa	ISO 527-1/-2
Strain at break	2.3 / —	%	ISO 527-1/-2
Charpy impact strength (+23°C)	46 / —	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8 / —	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.4 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
ELECTRICAL PROPERTIES			
	DRY / COND		
Comparative tracking index	600 / —	V	IEC 60112



Akulon[®] Ultraflow XG—FKGS6/A

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
OTHER PROPERTIES	DRY / COND		
Density	1430 / —	kg/m³	ISO 1183

