

Durethan® BKV30H2.0EF

PA6—GF30

30% Glass Reinforced, Injection Molding, Heat Stabilized, Improved flow

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.24 / *	%	ISO 294-4
Molding shrinkage (normal)	0.69 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	9400 / 5500	MPa	ISO 527-1/-2
Stress at break	170 / 100	MPa	ISO 527-1/-2
Strain at break	3 / 5.8	%	ISO 527-1/-2
Flexural modulus	8800 / 5000	MPa	ISO 178
Flexural strength	260 / 160	MPa	ISO 178
Tensile modulus (200°C)	2980	MPa	ISO 527-1/-2
Charpy impact strength (+23°C)	70 / 80	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	55 / 55	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 15	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	10 / 15	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	221 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	219 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10



Durethan® BKV30H2.0EF

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10

ELECTRICAL PROPERTIES	DRY / COND		
Electric strength	33 / 25	kV/mm	IEC 60243-1
Comparative tracking index	400 / -	V	IEC 60112

OTHER PROPERTIES	DRY / COND		
Water absorption	7 / *	%	Sim. to ISO 62
Humidity absorption	2.1 / *	%	Sim. to ISO 62
Density	1350 / -	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250-290	°C	
Mold temperature	80-120	°C	

