

# Durethan® ECOBKV60XF

## PA6—GF60

60% Glass Reinforced, Injection Molding, Heat Stabilized, Improved flow, Recycled Content

### Sustainability

Mass balanced  
Recycled based

| PROPERTIES                                   | TYPICAL DATA      | UNIT   | TEST METHOD    |
|----------------------------------------------|-------------------|--------|----------------|
| <b>RHEOLOGICAL PROPERTIES</b>                |                   |        |                |
|                                              | <b>DRY / COND</b> |        |                |
| Molding shrinkage (parallel)                 | 0.25 / *          | %      | ISO 294-4      |
| Molding shrinkage (normal)                   | 0.52 / *          | %      | ISO 294-4      |
| <b>MECHANICAL PROPERTIES</b>                 |                   |        |                |
|                                              | <b>DRY / COND</b> |        |                |
| Tensile modulus                              | 20200 / 13000     | MPa    | ISO 527-1/-2   |
| Stress at break                              | 215 / 140         | MPa    | ISO 527-1/-2   |
| Strain at break                              | 2.3 / 2.8         | %      | ISO 527-1/-2   |
| Flexural modulus                             | 18500 / 14000     | MPa    | ISO 178        |
| Flexural strength                            | 350 / 230         | MPa    | ISO 178        |
| Tensile modulus (200°C)                      | 5760              | MPa    | ISO 527-1/-2   |
| Charpy impact strength (+23°C)               | 88 / –            | kJ/m²  | ISO 179/1eU    |
| Charpy notched impact strength (+23°C)       | 15 / –            | kJ/m²  | ISO 179/1eA    |
| Izod notched impact strength (+23°C)         | 15 / –            | kJ/m²  | ISO 180/1A     |
| <b>THERMAL PROPERTIES</b>                    |                   |        |                |
|                                              | <b>DRY / COND</b> |        |                |
| Melting temperature (10°C/min)               | 221 / *           | °C     | ISO 11357-1/-3 |
| Temp. of deflection under load (1.80 MPa)    | 208 / *           | °C     | ISO 75-1/-2    |
| Temp. of deflection under load (0.45 MPa)    | 217 / *           | °C     | ISO 75-1/-2    |
| Coeff. of linear therm. expansion (parallel) | 0.11 / *          | E-4/°C | ISO 11359-1/-2 |



Durethan® ECOBKV60XF

| PROPERTIES                                 | TYPICAL DATA | UNIT   | TEST METHOD          |
|--------------------------------------------|--------------|--------|----------------------|
| Coeff. of linear therm. expansion (normal) | 0.85 / *     | E-4/°C | ISO 11359-1/-2       |
|                                            |              |        |                      |
| OTHER PROPERTIES                           | DRY / COND   |        |                      |
| Density                                    | 1690 / –     | kg/m³  | ISO 1183             |
|                                            |              |        |                      |
| PROCESSING RECOMMENDATIONS                 | VALUE        |        |                      |
| Drying temperature dry air dryer           | 80           | °C     |                      |
| Drying time dry air dryer                  | 2–6          | h      |                      |
| Residual moisture content                  | 0.05–0.15    | %      | acc. to Karl Fischer |
| Melt temperature (Tmin – Tmax)             | 270–290      | °C     |                      |
| Mold temperature                           | 80–120       | °C     |                      |

