

Durethan® ECOBKV25FN27

PA6—GX25 FR(30)

Injection Molding, 25% Glass Reinforced, Flame Retardant (halogen free), Heat Stabilized, Recycled Content

Sustainability

Mass balanced
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.6 / *	%	ISO 294-4
Molding shrinkage (normal)	0.7 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	5600 / 2300	MPa	ISO 527-1/-2
Stress at break	85 / 40	MPa	ISO 527-1/-2
Strain at break	3.2 / 25	%	ISO 527-1/-2
Flexural modulus	5100 / 2300	MPa	ISO 178
Flexural strength	140 / 70	MPa	ISO 178
Charpy impact strength (+23°C)	30 / 70	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	<10 / <10	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	<10 / <10	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	170 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.5 / *	E-4/°C	ISO 11359-1/-2



Durethan® ECOBKV25FN27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Coeff. of linear therm. expansion (normal)	0.9 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Oxygen index	27 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.75 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5 / -	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	725 / -	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.75 / -	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	725 / -	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	1.5 / -	mm	IEC 60695-2-13

ELECTRICAL PROPERTIES**DRY / COND**

Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
Electric strength	30 / -	kV/mm	IEC 60243-1
Comparative tracking index	550 / -	V	IEC 60112

OTHER PROPERTIES**DRY / COND**

Water absorption	7 / *	%	Sim. to ISO 62
Humidity absorption	2.1 / *	%	Sim. to ISO 62
Density	1340 / -	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS**VALUE**

Drying temperature dry air dryer	80	°C	
----------------------------------	----	----	--



Durethan® ECOBKV25FN27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.07	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250–270	°C	
Mold temperature	80–100	°C	

