

Durethan® DPBKV60H2.0EF

PA6—GF60

60% Glass Reinforced, Injection Molding, Heat Stabilized, Improved flow

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.28 / *	%	ISO 294-4
Molding shrinkage (normal)	0.46 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	20500 / 13100	MPa	ISO 527-1/-2
Stress at break	230 / 150	MPa	ISO 527-1/-2
Strain at break	2.4 / 3.1	%	ISO 527-1/-2
Flexural modulus	20000 / 13100	MPa	ISO 178
Flexural strength	370 / 245	MPa	ISO 178
Tensile modulus (200°C)	6050	MPa	ISO 527-1/-2
Charpy impact strength (+23°C)	90 / 90	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	90 / 90	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	16 / 20	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	16 / -	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	16 / 20	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	221 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	213 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.12 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.75 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10



Durethan® DPBKV60H2.0EF

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695-11-10

ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	5.3 / 11.2	—	IEC 62631-2-1
Relative permittivity (1 MHz)	4.7 / 5.1	—	IEC 62631-2-1
Dissipation factor (100 Hz)	164 / 2150	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	177 / 651	E-4	IEC 62631-2-1
Volume resistivity	5.8E12 / 8E9	Ohm*m	IEC 62631-3-1
Electric strength	33 / 33	kV/mm	IEC 60243-1
Comparative tracking index	600 / —	V	IEC 60112

OTHER PROPERTIES	DRY / COND		
Water absorption	3.6 / *	%	Sim. to ISO 62
Humidity absorption	1.1 / *	%	Sim. to ISO 62
Density	1720 / —	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Residual moisture content	0.05-0.15	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	270-290	°C	
Mold temperature	80-120	°C	

