

Tepex[®] dynalite 202–C200(x)/45%

PA6–CF56

Tepex[®] dynalite 202–C200(x)/45%

3K Carbon – PA6 consolidated composite laminate

The datasheet is valid for this specific composition only, the characteristics of composites depend on reinforcement level and fiber orientation. Non-standard thickness may alter some or all of these properties. The data listed here are given as average product properties and should not be used to establish specification limits nor used alone as basis of design. The underlying tests were conducted at room temperature and (where possible) with 2 mm specimen thickness. For tensile and flexural tests a specimen width of 25 mm was used and is highly recommended to achieve representative results.

Tepex[®]
BOND
 LAMINATES
 A company of Envalior

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
LAYUP	VALUE		
Fiber	3K Carbon		
Weaving style	Twill 2/2		DIN ISO 9354
Area weight (dry fabric)	200	g/m ²	DIN EN 12127
Weight rate (0°/90°)	50/50	%/%	
Polymer	Polyamide 6 (PA6)		
Fiber volume content	45	vol.-%	nominal
Thickness per layer	0.25	mm	nominal
MECHANICAL PROPERTIES	DRY / COND		
Flexural Modulus	43 / –	GPa	ISO 14125
Flexural Strength	750 / –	MPa	ISO 14125
THERMAL PROPERTIES	DRY / COND		
Density	1420 / –	kg/m ³	ISO 1183
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3

