

Novamid[®] 1015C

PA6

Low Viscosity, Injection Molding

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	150 / *	cm ³ /g	ISO 307, 1157, 1628



Novamid® 1015C

Viscosity–shear rate

