

Novamid[®] 1015GT30 BK37

PA6—I—GF30

Improved Impact, Glass Reinforced

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage [parallel]	0.5 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.4 / *	%	Sim. to ISO 294-4
MECHANICAL PROPERTIES	DRY / COND		
Strain at break	7 / –	%	ISO 527-1/-2
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Water absorption	1.8 / *	%	Sim. to ISO 62
Density	1330 / –	kg/m ³	ISO 1183

