

Novamid® 1015GH35 BK37

PA6—GF35

35% Glass Reinforced, Heat Stabilized, Injection Molding

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	1 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	11400 / 6700	MPa	ISO 527-1/-2
Stress at break	190 / 125	MPa	ISO 527-1/-2
Strain at break	2.6 / 5	%	ISO 527-1/-2
Flexural modulus	9800 / 6800	MPa	ISO 178
Flexural strength	295 / 200	MPa	ISO 178
Charpy impact strength (+23°C)	96 / 100	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 24	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	206 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
ELECTRICAL PROPERTIES			
	DRY / COND		
Relative permittivity (100Hz)	4 / —	—	IEC 62631-2-1
Relative permittivity (1 MHz)	4 / —	—	IEC 62631-2-1
Dissipation factor (100 Hz)	110 / —	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	190 / —	E-4	IEC 62631-2-1
Volume resistivity	7E12 / —	Ohm*m	IEC 62631-3-1



Novamid® 1015GH35 BK37

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Surface resistivity	– / 3E13	Ohm	IEC 62631–3–2
Electric strength	23 / –	kV/mm	IEC 60243–1
Comparative tracking index	400 / –	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1410 / –	kg/m³	ISO 1183

