

Novamid[®] 2430A

PA6/66

Extrusion Grade, Monofilament Grade, Highly lubricated, High Viscosity

Ideal for high tenacity & high transparency fishing monofilament extrusion.
High viscosity and high 66 content for larger diameter filament.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / –	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628



Novamid® 2430A

Viscosity–shear rate

