

Novamid[®] 2330J

PA6/66

Film Extrusion, Extrusion, Extrusion Grade

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
Melting temperature (10°C/min)	215 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	246 / *	cm³/g	ISO 307, 1157, 1628



Novamid[®] 2330J

Viscosity–shear rate

