

Novamid[®] 2020J

PA6/66

Extrusion, Medium/High Viscosity, Neat resin, Food Contact Quality

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Water absorption	13 / *	%	Sim. to ISO 62
Humidity absorption	3.5 / *	%	Sim. to ISO 62
Density	1130 / –	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	183 / *	cm³/g	ISO 307, 1157, 1628



Novamid® 2020J

Viscosity–shear rate

