

Novamid[®] 2430A-1

PA6/66

Extrusion, Film Extrusion, Lubricated, Food Contact Quality

Ideal for film extrusion processing.
Food Contact quality.
Enhance flexibility, transparency and stretch-ability of the film.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628



Novamid[®] 2430A-1

Viscosity-shear rate

