

Novamid[®] 2934A

PA6/66

Extrusion Grade, Monofilament Grade, Highly lubricated, Very High Viscosity

Ideal for monofilament extrusion. Super high viscosity. Easier to increase tenacity by stretching.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / –	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	278 / *	cm³/g	ISO 307, 1157, 1628

