

Stanyl[®] KS411

PA46

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
Melting temperature (10°C/min)	287 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Humidity absorption	3.7 / *	%	Sim. to ISO 62
Density	1180 / –	kg/m³	ISO 1183

