

Durethan® AKV25

PA66—GF25

25% Glass Reinforced, Injection Molding

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	9300 / 6000	MPa	ISO 527-1/-2
Stress at break	165 / 115	MPa	ISO 527-1/-2
Strain at break	3 / 6	%	ISO 527-1/-2
Flexural modulus	7400 / 5000	MPa	ISO 178
Flexural strength	265 / 170	MPa	ISO 178
Charpy impact strength (+23°C)	60 / 80	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	50 / 50	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 12	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m²	ISO 179/1eA
Izod notched impact strength (-40°C)	<10 / <10	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	263 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	240 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	250 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.1 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Oxygen index	23 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	650 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2 / -	mm	IEC 60695-2-12



Durethan® AKV25

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES			
DRY / COND			
Relative permittivity (100Hz)	4 / 10	—	IEC 62631-2-1
Relative permittivity (1 MHz)	4 / 4	—	IEC 62631-2-1
Dissipation factor (100 Hz)	110 / 2150	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	190 / 750	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
Electric strength	40 / 35	kV/mm	IEC 60243-1
Comparative tracking index	600 / —	V	IEC 60112
OTHER PROPERTIES			
DRY / COND			
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	2.1 / *	%	Sim. to ISO 62
Density	1320 / —	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
DRY / COND			
Viscosity number	146 / *	cm³/g	ISO 307, 1157, 1628
PROCESSING RECOMMENDATIONS			
VALUE			
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	280-300	°C	
Mold temperature	80-120	°C	

