

Durethan® AKV230H2.0

PA66—I—GF30

30% Glass Reinforced, Injection Molding, Heat Stabilized, Improved Impact

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.5 / *	%	ISO 294-4
Molding shrinkage (normal)	0.85 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	8000 / 5100	MPa	ISO 527-1/-2
Stress at break	130 / 85	MPa	ISO 527-1/-2
Strain at break	4 / 6.5	%	ISO 527-1/-2
Flexural modulus	7000 / 4600	MPa	ISO 178
Flexural strength	200 / 135	MPa	ISO 178
Charpy impact strength (+23°C)	75 / 80	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	85 / 85	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	20 / 28	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	15 / 15	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	20 / 28	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	262 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
	DRY / COND		
Density	1290 / -	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS			
	VALUE		
Drying temperature dry air dryer	80	°C	



Durethan® AKV230H2.0

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	280-300	°C	
Mold temperature	80-120	°C	

