

Durethan® AKV30XTS2

PA66—GF30

30% Glass Reinforced, Injection Molding, Heat Stabilized, Excellent Surface Properties

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.35 / *	%	ISO 294-4
Molding shrinkage (normal)	0.7 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	10000 / 6500	MPa	ISO 527-1/-2
Stress at break	190 / 120	MPa	ISO 527-1/-2
Strain at break	3 / 7.5	%	ISO 527-1/-2
Flexural modulus	9500 / 6500	MPa	ISO 178
Flexural strength	280 / 195	MPa	ISO 178
Tensile modulus (200°C)	2780	MPa	ISO 527-1/-2
Charpy impact strength (+23°C)	60 / 95	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	50 / 45	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	<10 / 12	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	<10 / 12	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	235 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	250 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.23 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.9 / *	E-4/°C	ISO 11359-1/-2



Durethan® AKV30XTS2

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES			
Comparative tracking index	600 / –	V	IEC 60112
OTHER PROPERTIES			
Water absorption	6.3 / *	%	Sim. to ISO 62
Density	1380 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS			
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	270–290	°C	
Mold temperature	80–100	°C	
admissible residence time at Tmax	<5	min	

