

Tepex[®] dynalite 101–RG600(x)/47%

PA66–GF66

Tepex[®] dynalite 101–RG600(x)/47%

Roving Glass – PA66 consolidated composite laminate

The datasheet is valid for this specific composition only, the characteristics of composites depend on reinforcement level and fiber orientation. Non-standard thickness may alter some or all of these properties. The data listed here are given as average product properties and should not be used to establish specification limits nor used alone as basis of design. The underlying tests were conducted at room temperature and (where possible) with 2 mm specimen thickness. For tensile and flexural tests a specimen width of 25 mm was used and is highly recommended to achieve representative results.

Tepex[®]
BOND
 LAMINATES
 A company of Envalior

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
LAYUP	VALUE		
Fiber	E-Glass 1200 tex		
Weaving style	Twill 2/2		DIN ISO 9354
Area weight (dry fabric)	600	g/m ²	DIN EN 12127
Weight rate (0°/90°)	50/50	%/%	
Polymer	Polyamide 6.6 (PA66)		
Fiber volume content	47	vol.-%	nominal
Thickness per layer	0.5	mm	nominal
MECHANICAL PROPERTIES	DRY / COND		
Tensile Modulus	23 / 19	GPa	ISO 527–4/5
Tensile Strength	380 / 370	MPa	ISO 527–4/5
Elongation at Break	2 / 2.1	%	ISO 527–4/5
Flexural Modulus	20 / 17	GPa	ISO 14125
Flexural Strength	600 / 490	MPa	ISO 14125



Tepex[®] dynalite 101–RG600(x)/47%

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES		DRY / COND	
Density	1810 / –	kg/m³	ISO 1183
Melting temperature (10°C/min)	260 / *	°C	ISO 11357–1/–3
Heat deflection temperature (0.1% flex. Modulus)	255	°C	ISO 75–1/3
CLTE –35°C to 23°C (0°)	15.1	E–4/°C	ISO 11359–1/–2
CLTE 23°C to 80°C (0°)	15.1	E–4/°C	ISO 11359–1/–2

