

Arnite[®] TV4 261/A HR

PBT–GF30

30% Glass Reinforced, Hydrolysis resistant

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Molding shrinkage [normal]	1.2	%	Sim. to ISO 294–4
Molding shrinkage [parallel]	0.33	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	9250	MPa	ISO 527–1/–2
Stress at break	130	MPa	ISO 527–1/–2
Strain at break	3	%	ISO 527–1/–2
Charpy impact strength (+23°C)	60	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	45	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	8	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
	VALUE		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.27	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.65	E–4/°C	ISO 11359–1/–2
ELECTRICAL PROPERTIES			
	VALUE		
Relative permittivity (100Hz)	3.9	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.7	–	IEC 62631–2–1
Dissipation factor (100 Hz)	25	E–4	IEC 62631–2–1



Arnite[®] TV4 261/A HR

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Dissipation factor (1 MHz)	170	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	400	V	IEC 60112
Comparative tracking index (PLC)	1	class	UL 746A

OTHER PROPERTIES	VALUE		
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1520	kg/m³	ISO 1183

