

Arnite[®] TV4 261 /G

PBT–GF30

30% Glass Reinforced, Glueable

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume–flow rate	18	cm ³ /10min	ISO 1133
Temperature	250	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [normal]	1.2	%	Sim. to ISO 294–4
Molding shrinkage [parallel]	0.33	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	10000	MPa	ISO 527–1/–2
Stress at break	140	MPa	ISO 527–1/–2
Strain at break	2.8	%	ISO 527–1/–2
Charpy impact strength (+23°C)	60	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	10	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES		VALUE	
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.35	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.7	E–4/°C	ISO 11359–1/–2
Oxygen index	20	%	ISO 4589–1/–2



Arnite[®] TV4 261 /G

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES		VALUE	
Relative permittivity (100Hz)	3.9	—	IEC 62631-2-1
Relative permittivity (1 MHz)	3.7	—	IEC 62631-2-1
Dissipation factor (100 Hz)	25	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	170	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	400	V	IEC 60112
Comparative tracking index (PLC)	1	class	UL 746A
OTHER PROPERTIES		VALUE	
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1520	kg/m³	ISO 1183



Arnite® TV4 261 /G

Viscosity-shear rate

