

Pocan[®] B3215XF

PBT—GF10

10% Glass Reinforced, Injection Molding, Improved flow, Improved Impact

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume—flow rate	32	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1.1	%	ISO 294-4
Molding shrinkage (parallel)	0.9	%	ISO 294-4
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	4350	MPa	ISO 527-1/-2
Stress at break	80	MPa	ISO 527-1/-2
Strain at break	4	%	ISO 527-1/-2
Flexural modulus	4250	MPa	ISO 178
Flexural strength	135	MPa	ISO 178
Flexural strain at flexural strength	4.8	%	ISO 178-A
Charpy impact strength (+23°C)	40	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	30	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4.7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	4.1	kJ/m ²	ISO 179/1eA
Izod impact strength (+23°C)	30	kJ/m ²	ISO 180/1U
Izod impact strength (-30°C)	25	kJ/m ²	ISO 180-1U
THERMAL PROPERTIES		VALUE	
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	185	°C	ISO 75-1/-2



Property Data


Pocan[®] B3215XF

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Temp. of deflection under load (0.45 MPa)	215	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.6	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.4	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10

ELECTRICAL PROPERTIES	VALUE		
Comparative tracking index	350	V	IEC 60112

OTHER PROPERTIES	VALUE		
Density	1350	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250-270	°C	
Mold temperature	80-100	°C	



Pocan[®] B3215XF

Viscosity—shear rate

