

Pocan[®] B7616

(PBT+PC)—GF15

15% Glass Reinforced, Injection Molding, Excellent Surface Properties, Low Warpage

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume—flow rate	17	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	0.5	%	ISO 294-4
Molding shrinkage (parallel)	0.7	%	ISO 294-4
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	4600	MPa	ISO 527-1/-2
Stress at break	75	MPa	ISO 527-1/-2
Strain at break	4.2	%	ISO 527-1/-2
Flexural modulus	4500	MPa	ISO 178
Flexural strength	130	MPa	ISO 178
Flexural strain at flexural strength	4.7	%	ISO 178-A
Charpy impact strength (+23°C)	45	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	3.5	kJ/m ²	ISO 179/1eA
Izod impact strength (+23°C)	35	kJ/m ²	ISO 180/1U
Izod impact strength (-30°C)	40	kJ/m ²	ISO 180-1U
THERMAL PROPERTIES		VALUE	
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	105	°C	ISO 75-1/-2



Pocan[®] B7616

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Temp. of deflection under load (0.45 MPa)	135	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.5	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	750	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2	mm	IEC 60695-2-12

ELECTRICAL PROPERTIES	VALUE		
Relative permittivity (100Hz)	3.5	—	IEC 62631-2-1
Relative permittivity (1 MHz)	3.4	—	IEC 62631-2-1
Dissipation factor (100 Hz)	10	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	130	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	34	kV/mm	IEC 60243-1
Comparative tracking index	200	V	IEC 60112

OTHER PROPERTIES	VALUE		
Water absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1350	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	



Pocan[®] B7616

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250–270	°C	
Mold temperature	80–100	°C	

Viscosity–shear rate

