

Pocan[®] B3233HRLT

PBT—GF30

30% Glass Reinforced, Injection Molding, Hydrolysis resistant, Laser Weldable, Laser Transparent Black

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Molding shrinkage (normal)	0.8	%	ISO 294-4
Molding shrinkage (parallel)	0.3	%	ISO 294-4
MECHANICAL PROPERTIES	VALUE		
Tensile modulus	10000	MPa	ISO 527-1/-2
Stress at break	140	MPa	ISO 527-1/-2
Strain at break	2.8	%	ISO 527-1/-2
Flexural modulus	9600	MPa	ISO 178
Flexural strength	230	MPa	ISO 178
Flexural strain at flexural strength	3.2	%	ISO 178-A
Charpy impact strength (+23°C)	60	kJ/m ²	ISO 179/1eU
Izod impact strength (+23°C)	53	kJ/m ²	ISO 180/1U
THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1	E-4/°C	ISO 11359-1/-2
ELECTRICAL PROPERTIES	VALUE		
Comparative tracking index	275	V	IEC 60112



Pocan[®] B3233HRLT

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
OTHER PROPERTIES			
Density	1520	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS			
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	60–80	°C	

