

Pocan[®] KU1-7313

(PBT+PET)-GF15

15% Glass Reinforced, Injection Molding, Excellent Surface Properties

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume-flow rate	18	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1	%	ISO 294-4
Molding shrinkage (parallel)	0.5	%	ISO 294-4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	6100	MPa	ISO 527-1/-2
Stress at break	110	MPa	ISO 527-1/-2
Strain at break	3.2	%	ISO 527-1/-2
Flexural strain at flexural strength	3.8	%	ISO 178-A
Charpy impact strength (+23°C)	30	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	30	kJ/m ²	ISO 179/1eU
Izod impact strength (-30°C)	25	kJ/m ²	ISO 180-1U
THERMAL PROPERTIES			
	VALUE		
Temp. of deflection under load (1.80 MPa)	185	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.5	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.1	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10



Pocan® KU1–7313

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Thickness tested	1.5	mm	IEC 60695–11–10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	3	mm	IEC 60695–11–10
Oxygen index	22	%	ISO 4589–1/–2
Glow Wire Flammability Index GWFI	750	°C	IEC 60695–2–12
GWFI (Thickness (1) tested)	2	mm	IEC 60695–2–12

ELECTRICAL PROPERTIES	VALUE		
Relative permittivity (100Hz)	3.6	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.5	–	IEC 62631–2–1
Dissipation factor (100 Hz)	20	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	170	E–4	IEC 62631–2–1
Volume resistivity	>1E13	Ohm*m	IEC 62631–3–1
Surface resistivity	>1E15	Ohm	IEC 62631–3–2
Electric strength	24	kV/mm	IEC 60243–1
Comparative tracking index	225	V	IEC 60112

OTHER PROPERTIES	VALUE		
Water absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1430	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	80–100	°C	



Pocan[®] KU1-7313

Viscosity-shear rate

