

Arnitel[®] EL150

TPC—ET

Injection Molding

Arnitel EL150 is a very low modulus grade with nominal hardness of 20D. Material can be processed by many conventional thermoplastics processing techniques such as injection molding.

It is important to note that in a certain periods, clumps can be formed due to excessive storage conditions such as packing type, stacking, extreme temperature. Pl. refer injection molding recommendations

Food contact use – Not Applicable.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume—flow rate	76	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [parallel]	0.7	%	Sim. to ISO 294–4
Molding shrinkage [normal]	1	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES		VALUE	
Shore D Hardness (3s)	19	—	ISO 868
Shore D Hardness (15s)	18	—	ISO 868
Shore A Hardness (3s)	80	—	ISO 868
Shore A Hardness (15s)	79	—	ISO 868
Tensile modulus	16	MPa	ISO 527–1/–2
Stress at break	14.4	MPa	ISO 527–1/–2
Nominal strain at break	980	%	ISO 527–1/–2
Stress at 5% strain	0.8	MPa	ISO 527–1/–2
Stress at 10% strain	1.4	MPa	ISO 527–1/–2
Stress at 50% strain	3.1	MPa	ISO 527–1/–2



Arnitel[®] EL150

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at 100% strain	3.8	MPa	ISO 527-1/-2
THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	165	°C	ISO 11357-1/-3
OTHER PROPERTIES	VALUE		
Density	1060	kg/m³	ISO 1183
Humidity absorption	0.12	%	Sim. to ISO 62

