

Arnitel[®] CM622

TPC-ES

60 Shore D, Extrusion

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Melt volume-flow rate	9	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES	VALUE		
Shore D Hardness (3s)	61	—	ISO 868
Shore D Hardness (15s)	61	—	ISO 868
Tensile modulus	235	MPa	ISO 527-1/-2
Stress at break	34	MPa	ISO 527-1/-2
Nominal strain at break	400	%	ISO 527-1/-2
Stress at 5% strain	14	MPa	ISO 527-1/-2
Stress at 10% strain	19	MPa	ISO 527-1/-2
Stress at 50% strain	22	MPa	ISO 527-1/-2
Stress at 100% strain	21	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	8	kJ/m ²	ISO 179/1eA
Izod notched impact strength (-30°C)	6	kJ/m ²	ISO 180/1A
Flexural modulus	270	MPa	ISO 178
Compression Set under constant strain at 23 °C	19	%	ISO 815
Compression Set under constant strain at 70 °C	37	%	ISO 815

MECHANICAL PROPERTIES (DIE CUTTING)

VALUE



Arnitel[®] CM622

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at break (normal)	40	MPa	ISO 527-1/-2
Stress at 100% strain (normal)	17	MPa	ISO 527-1/-2
Tear strength (normal)	171	kN/m	ISO 34-1; Method B
Tear strength (parallel)	191	kN/m	ISO 34-1; Method B
Strain at break (normal)	640	%	ISO 527-1/-2
THERMAL PROPERTIES		VALUE	
Melting temperature (10°C/min)	208	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	90	°C	ISO 306
Vicat softening temperature (50°C/h 10N)	190	°C	ISO 306
ELECTRICAL PROPERTIES		VALUE	
Electric strength	23.5	kV/mm	IEC 60243-1
Comparative tracking index	600	V	IEC 60112
OTHER PROPERTIES		VALUE	
Density	1270	kg/m³	ISO 1183
Apparent density	700	kg/m³	ISO 60
Humidity absorption	0.1	%	Sim. to ISO 62

