

Arnitel[®] PM460-H

TPC-ET

Injection Molding, Heat Stabilized

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Melt volume-flow rate	9.6	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES	VALUE		
Shore D Hardness (3s)	45	—	ISO 868
Tensile modulus	120	MPa	ISO 527-1/-2
Stress at break	19.5	MPa	ISO 527-1/-2
Nominal strain at break	205	%	ISO 527-1/-2
Stress at 5% strain	5.4	MPa	ISO 527-1/-2
Stress at 10% strain	8.4	MPa	ISO 527-1/-2
Stress at 50% strain	13.3	MPa	ISO 527-1/-2
Stress at 100% strain	15.5	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	N	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-30°C)	N	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	216	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	65	°C	ISO 75-1/-2

OTHER PROPERTIES**VALUE**

Arnitel[®] PM460–H

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Density	1210	kg/m³	ISO 1183

